

Dam: Hongpo

Country: China

River: Qinggoushui

DMS Co-ordinates: Unknown

DD Co-ordinates: Unknown

Owner/Client: Xishan Xingyu Water Resources Corporation

Designer/Engineer: Insitute of Investigation and Design of Water Resources and Hydropower, Kunming City

Contractor: 8th Construction Bureau, MOE & MWR

Purpose (code): W

Site start: 01.10.1997

RCC start: 24.07.1998

RCC completion: 23.11.1999

Site completion: 30.12.1999

Height (m): 55

Length (m): 244

Volume of RCC ($\text{m}^3 \times 10^3$): 71

Total volume ($\text{m}^3 \times 10^3$): 77

Reservoir capacity ($\text{m}^3 \times 10^6$): 3

Upstream slope: V

Forming of upstream face (code): (3')

Downstream slope: 0.50

Forming of downstream face (code): (1)

Spillway slope: 0.50

Forming of spillway face (code): (1)

Depth of layers (mm): 300

Depth of lifts (mm): 3000

Cement content (kg/m^3): 54

Pozzolan content (kg/m^3): 99

Code for pozzolan: (F)

RCCDAM Unique Serial No.: RCCDAM0222

Under Construction



RCCDAM0222UC

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines