

Dam: Kalashuke

Country: China

River: E'erqisi

DMS Co-ordinates: Unknown

DD Co-ordinates: Unknown

Owner/Client: Department of Water Resources, Xinjiang Province

Designer/Engineer: Xinjiang Design Institute for Water Conservancy and Hydropower

Contractor: 16th Construction Bureaux

Purpose (code): F H W

Site start: 01.01.2007

RCC start: 01.01.2010

RCC completion: 31.12.2013

Site completion: 31.12.2014

Height (m): 122

Length (m): 1489

Volume of RCC ($\text{m}^3 \times 10^3$): 2520

Total volume ($\text{m}^3 \times 10^3$): 2890

Reservoir capacity ($\text{m}^3 \times 10^6$): 2419

Upstream slope: Unknown

Forming of upstream face (code): Unknown

Downstream slope: 0.75

Forming of downstream face (code): Unknown

Spillway slope: 0.75

Forming of spillway face (code): Unknown

Depth of layers (mm): 300

Depth of lifts (mm): 3000

Cement content (kg/m^3): Unknown

Pozzolan content (kg/m^3): Unknown

Code for pozzolan: (F)

RCCDAM Unique Serial No.: RCCDAM0579

Completed Dam



RCCDAM0579CD

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines