

Dam: Amatisteros III

Country Spain

River Belén

36°51'45.22"N 02°28'3.73"W

36.86256 -2.467703

Owner/Client Junta de Andalucia

Designer/Engineer Confederacion Hidrografica del Sur

Contractor SACYR

Purpose (code) F

Site start 01.01.1991

RCC start 01.09.1991

RCC completion 30.12.1991

Site completion 31.12.1992

Height (m) 15

Length (m) 75

Volume of RCC (m³x10³) 4

Total volume (m³x10³) 5

Reservoir capacity (m³x10⁶) 1

Upstream slope V

Forming of upstream face (code) (3)

Downstream slope 0.75

Forming of downstream face (code) (3) \*

Spillway slope 0.75

Forming of spillway face (code) (3)

Depth of layers (mm) 300

Depth of lifts (mm) 300

Cement content (kg/m³) 73

Pozzolan content (kg/m³) 109

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM1066

### Completed Dam



RCCDAM1066CD

### Google Earth



RCCDAM1066GE

# Guide to Abbreviations

## Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

## Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
  - ' GEVR/GE-RCC
  - \* Stepped face

## Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines