

Dam: Baishiya

Country: China

River: Xijiang

21°51'39.54"N 108°2'11.07"E

21.860983 108.036407

Owner/Client: Quifeng Water Supply Co. of Fangchenggang City

Designer/Engineer: Insitute of Investigation and Design for Hydropower Projects, Guangxi Province

Contractor: *Unknown*

Purpose (code): H I W

Site start: 01.01.2004

RCC start: 01.01.2007

RCC completion: 31.12.2009

Site completion: 31.12.2012

Height (m): 74

Length (m): 190

Volume of RCC (m³x10³): 230

Total volume (m³x10³): 240

Reservoir capacity (m³x10⁶): 26

Upstream slope: *Unknown*

Forming of upstream face (code): *Unknown*

Downstream slope: 0.75

Forming of downstream face (code): *Unknown*

Spillway slope: *Unknown*

Forming of spillway face (code): *Unknown*

Depth of layers (mm): *Unknown*

Depth of lifts (mm): *Unknown*

Cement content (kg/m³): *Unknown*

Pozzolan content (kg/m³): *Unknown*

Code for pozzolan: *Unknown*

RCCDAM Unique Serial No.: RCCDAM0424

Completed Dam



RCCDAM0424CD

Google Earth



RCCDAM0424GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines