Dam:	Dodairagawa	Country	Japan
River	Kabura	36°14'6.34"N 138°40'41.44"E	36.235092 138.678177
Owner/Client	Gunma Prefecture		
Designer/Engineer	Gunma-ken		
Contractor	Kumagi-Gumi Co Ltd., Kajima Co Ltd, Shimizu Construction Co Ltd., and Sada Construction Co Ltd. (J.V.)		

Purpose (code)	F W
Site start	17.03.1986
RCC start	01.06.1988
RCC completion	31.01.1990
Site completion	01.03.1992
Height (m)	70
Length (m)	300
Volume of RCC (m^3x10^3)	167
Total volume (m^3x10^3)	350
Reservoir capacity (m^3x10^6)	5
Upstream slope	V 0.40
Forming of upstream face (code)	(1) (1)
Downstream slope	0.75
Forming of downstream face (code)	(1)
Spillway slope	0.75
Forming of spillway face (code)	(1)
Depth of layers (mm)	180
Depth of lifts (mm)	500
Cement content (kg/m^3)	96
Pozzolan content (kg/m^3)	24
Code for pozzolan	(F)
RCCDAM Unique Serial No.	RCCDAM0062

Completed Dam



RCCDAM0062CD

Google Earth



RCCDAM0062GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines