Dam:	El Zapotillo	Country	Mexico
River	Verde	21°08'12.98"N 102°48'20.96"W	21.136938 -102.805824
Owner/Client	CNA (Comisión Nacional del Agua)		
Designer/Engineer	AYESA		
Contractor	J.V. of FCC (Spain) and La Peninsular (Mexico)		

Purpose (code)	W
Site start	01.01.2009
RCC start	01.11.2011
RCC completion	31.12.2024
Site completion	30.12.2024
Height (m)	80
Length (m)	271
Volume of RCC (m^3x10^3)	1100
Total volume (m^3x10^3)	1200
Reservoir capacity (m^3x10^6)	910
Upstream slope	V
Forming of upstream face (code)	(3')
Downstream slope	0.83
Forming of downstream face (code)	(3) *
Spillway slope	0.83
Forming of spillway face (code)	(3) *
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	60 to 80
Pozzolan content (kg/m^3)	50 to 70
Code for pozzolan	(S)
RCCDAM Unique Serial No.	RCCDAM0645

Under Construction



RCCDAM0645UC

Google Earth



RCCDAM0645GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines