Dam:	Elkwater Fork	Country	USA
River	Tygart Tributory	38°35'54.62"N 80°3'40.03"W	38.598507 -80.061119
Owner/Client	Natural Resources Conservation Service		
Designer/Engineer	Gannet Fleming		
Contractor	Heeter Construction		

Purpose (code)	W
Site start	01.01.2006
RCC start	11.04.2007
RCC completion	10.08.2007
Site completion	31.12.2007
Height (m)	39
Length (m)	204
Volume of RCC (m^3x10^3)	106
Total volume (m^3x10^3)	113
Reservoir capacity (m^3x10^6)	3
Upstream slope	V
Forming of upstream face (code)	(8)
Downstream slope	0.80
Forming of downstream face (code)	(3) *
Spillway slope	0.80
Forming of spillway face (code)	(1) *
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	59
Pozzolan content (kg/m^3)	89
Code for pozzolan	(F)
RCCDAM Unique Serial No.	RCCDAM0387

Under Construction



RCCDAM0387UC

Completed Dam



RCCDAM0387CD

Google Earth



RCCDAM0387GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines