Dam:	Ghasre Ghand (formerly Zirdan)	Country	Iran
River	Kajoo	25°55'19.60"N 60°35'37.44"E	25.922112 60.593735
Owner/Client	Sistan & Balouchestan Water Authority		
Designer/Engineer	Abfan-Pazhouhab Consulting Engineers		
Contractor	Jahan Kowsar Co		

Purpose (code)	I W
Site start	01.11.2002
RCC start	01.08.2007
RCC completion	01.08.2010
Site completion	01.11.2010
Height (m)	65
Length (m)	350
Volume of RCC (m^3x10^3)	265
Total volume (m^3x10^3)	437
Reservoir capacity (m^3x10^6)	207
Upstream slope	*Unknown*
Forming of upstream face (code)	(5)
Downstream slope	*Unknown*
Forming of downstream face (code)	(3) *
Spillway slope	*Unknown*
Forming of spillway face (code)	*Unknown*
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	98
Pozzolan content (kg/m^3)	42
Code for pozzolan	(N)
RCCDAM Unique Serial No.	RCCDAM0467

Under Construction

RCCDAM0467UC

Google Earth

RCCDAM0467GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines