Dam:	Guangzhou PSS- Lower dam	Country	China
River	Liuxihe	23°46'20.57"N 113°57'29.22"E	23.772381 113.958115
Owner/Client	China Southern Power Grid		
Designer/Engineer	Guangdong Provincial Design Institute for Water Conservancy and Electric Power		
Contractor	14th Construction Bureau, MOE & MWR		

Purpose (code)	H
Site start	01.12.1994
RCC start	01.10.1991
RCC completion	30.12.1992
Site completion	31.10.2000
Height (m)	61
Length (m)	153
Volume of RCC (m^3x10^3)	32
Total volume (m^3x10^3)	57
Reservoir capacity (m^3x10^6)	30
Upstream slope	V
Forming of upstream face (code)	(1)
Downstream slope	0.70
Forming of downstream face (code)	(3) *
Spillway slope	ogee 0.78
Forming of spillway face (code)	(1) (1)
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	62
Pozzolan content (kg/m^3)	108
Code for pozzolan	(F)
RCCDAM Unique Serial No.	RCCDAM0111

Google Earth



RCCDAM0111GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines