

Dam: Julius Nyerere (formerly Rufiji) Country Tanzania

River Rufiji 7°48'10.58"S 37°51'2.81"E -7.802939 37.85078

Owner/Client TANESCO (Tanzania Electric Supply Company Ltd.)

Designer/Engineer AC-EE (Arab Contractors and Elsewedy Electric S.A.E. JV)

Contractor AC-EE (Arab Contractors and Elsewedy Electric S.A.E. JV) (SinoHydro Co. Ltd. (11th Construction Bureau) dam sub-Contractor)

Purpose (code) H

Site start 15.12.2018

RCC start 20.10.2020

RCC completion 30.12.2022

Site completion 30.12.2023

Height (m) 134

Length (m) 1025

Volume of RCC (m³x10³) 1420

Total volume (m³x10³) 1940

Reservoir capacity (m³x10⁶) 3680

Upstream slope 0.20

Forming of upstream face (code) (3')

Downstream slope 0.75

Forming of downstream face (code) (3') *

Spillway slope 0.75

Forming of spillway face (code) (12)

Depth of layers (mm) *Unknown*

Depth of lifts (mm) *Unknown*

Cement content (kg/m³) 93

Pozzolan content (kg/m³) 62

Code for pozzolan (F)

RCCDAM Unique Serial No. RCCDAM1082

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines