

Dam: Ouldjet Mellegue

Country: Algeria

River: Mellegue

35°58'36.09"N 08°01'41.76"E

35.976692 8.028267

Owner/Client: ANBT (Agence Nationale des Barrages et Transfert)

Designer/Engineer: Tractabel Engineering

Contractor: Cosider TP

Purpose (code): I W

Site start: 04.10.2011

RCC start: 01.01.2013

RCC completion: 31.12.2017

Site completion: 31.12.2018

Height (m): 51

Length (m): 900

Volume of RCC (m³x10³): 245

Total volume (m³x10³): 320

Reservoir capacity (m³x10⁶): 155

Upstream slope: V

Forming of upstream face (code): (1)

Downstream slope: 0.80

Forming of downstream face (code): (1)

Spillway slope: 0.80

Forming of spillway face (code): (1)

Depth of layers (mm): 300

Depth of lifts (mm): 300

Cement content (kg/m³): 110

Pozzolan content (kg/m³): 0

Code for pozzolan: (-)

RCCDAM Unique Serial No.: RCCDAM0652

Completed Dam



RCCDAM0652CD

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines