

Dam: Poço do Marruão

Country Brazil

River Riacho do Jorge

7°42'14.54"S 41°13'54.64"W

-7.704039 -41.231846

Owner/Client Insituto de Desenvolvimento do Piauí

Designer/Engineer CEC

Contractor Unknown

Purpose (code) I W

Site start 01.01.2007

RCC start 01.01.2008

RCC completion 31.12.2009

Site completion 30.06.2010

Height (m) 48

Length (m) 870

Volume of RCC (m³x10³) 293

Total volume (m³x10³) 306

Reservoir capacity (m³x10⁶) 293

Upstream slope Unknown

Forming of upstream face (code) Unknown

Downstream slope Unknown

Forming of downstream face (code) Unknown

Spillway slope Unknown

Forming of spillway face (code) Unknown

Depth of layers (mm) Unknown

Depth of lifts (mm) Unknown

Cement content (kg/m³) Unknown

Pozzolan content (kg/m³) Unknown

Code for pozzolan Unknown

RCCDAM Unique Serial No. RCCDAM0850

Completed Dam



RCCDAM0850CD

Google Earth



RCCDAM0850GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines