Dam:	Sierra Brava	Country	Spain
River	Pizarroso	39°11'36.22"N 5°38'39.84"W	39.193394 -5.6444
Owner/Client	Confederación Hidrográfica del Guadiana		
Designer/Engineer	PYCSA		
Contractor	Padros (OCP Construcciones) - now ACS Dragados		

Purpose (code)	I
Site start	01.12.1990
RCC start	01.06.1992
RCC completion	30.11.1993
Site completion	31.12.1993
Height (m)	54
Length (m)	835
Volume of RCC (m^3x10^3)	277
Total volume (m^3x10^3)	340
Reservoir capacity (m^3x10^6)	232
Upstream slope	0.05
Forming of upstream face (code)	(14)
Downstream slope	0.75
Forming of downstream face (code)	(14) *
Spillway slope	0.75
Forming of spillway face (code)	(14) *
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	80
Pozzolan content (kg/m^3)	140
Code for pozzolan	(F)
RCCDAM Unique Serial No.	RCCDAM0125

Under Construction

RCCDAM0125UC

Completed Dam

RCCDAM0125CD

Google Earth

RCCDAM0125GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines