

Dam: Tobetsu

Country Japan

River Tobetsu

43°19'3.71"N 141°33'46.23"E

43.317696 141.562836

Owner/Client Hokkaido Prefecture

Designer/Engineer Docon Co. Ltd.

Contractor Kajima Corp., Takenakadoboku and Iwakura J.V.

Purpose (code) F I W

Site start 01.10.2008

RCC start 01.06.2009

RCC completion 30.09.2010

Site completion 31.10.2012

Height (m) 52

Length (m) 432

Volume of RCC (m³x10³) 665

Total volume (m³x10³) 803

Reservoir capacity (m³x10⁶) 75

Upstream slope 0.80

Forming of upstream face (code) (5)

Downstream slope 0.80

Forming of downstream face (code) (5)

Spillway slope 0.80

Forming of spillway face (code) (1)

Depth of layers (mm) 250

Depth of lifts (mm) 750

Cement content (kg/m³) 100
80 60

Pozzolan content (kg/m³) 0 0

Code for pozzolan (-)

RCCDAM Unique Serial No. RCCDAM0471

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines