Dam:	Tukahe	Country	China
River	Lixian	22°36'31.79"N 102°15'22.86"E	22.608831 102.256348
Owner/Client	Datang International Power Generation Co. Ltd.		
Designer/Engineer	Beijing Hydropower Investigation, Design and Research Institute		
Contractor	Gezhouba Group 5th Company		

Purpose (code)	H
Site start	01.04.2004
RCC start	01.12.2005
RCC completion	31.12.2006
Site completion	31.12.2007
Height (m)	59
Length (m)	300
Volume of RCC (m^3x10^3)	255
Total volume (m^3x10^3)	570
Reservoir capacity (m^3x10^6)	78
Upstream slope	V
Forming of upstream face (code)	(3')
Downstream slope	*Unknown*
Forming of downstream face (code)	(3')
Spillway slope	*Unknown*
Forming of spillway face (code)	(3')
Depth of layers (mm)	300
Depth of lifts (mm)	3000
Cement content (kg/m^3)	65 93
Pozzolan content (kg/m^3)	110 113
Code for pozzolan	(S)
RCCDAM Unique Serial No.	RCCDAM0377

Completed Dam



RCCDAM0377CD

Google Earth



RCCDAM0377GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines