Dam:	Upper Yeywa (Kyaukme)	Country	Myanmar
River	Myitnge	22°14'31.57"N 97°06'6.84"E	22.242104 97.101898
Owner/Client	Department of Hydroelectric Power - Ministry of Electric Power		
Designer/Engineer	Lahmeyer/Stucky - AFRY		
Contractor	DHPI		

Purpose (code)	H
Site start	01.01.2015
RCC start	01.01.2024
RCC completion	31.12.2028
Site completion	31.12.2029
Height (m)	102
Length (m)	266
Volume of RCC (m^3x10^3)	532
Total volume (m^3x10^3)	580
Reservoir capacity (m^3x10^6)	341
Upstream slope	V
Forming of upstream face (code)	(3')
Downstream slope	0.80
Forming of downstream face (code)	(3') *
Spillway slope	0.80
Forming of spillway face (code)	(12)
Depth of layers (mm)	300
Depth of lifts (mm)	300
Cement content (kg/m^3)	*Unknown*
Pozzolan content (kg/m^3)	*Unknown*
Code for pozzolan	*Unknown*
RCCDAM Unique Serial No.	RCCDAM0720

Under Construction



RCCDAM0720UC

Google Earth



RCCDAM0720GE

Guide to Abbreviations

Purpose

E	Environmental
F	Flood control
G	Groundwater recharge
H	Flood control
I	Irrigation
N	Navigation
P	Pollution control
R	Recreation
W	Water supply

Facing method

(1)	Traditional concrete against formwork
(2)	Traditional concrete against formwork with external geomembrane
(3)	RCC against formwork
(4)	RCC against formwork with external geomembrane
(5)	Traditional concrete against precast concrete panels
(6)	Traditional concrete against precast concrete panels with geomembrane
(7)	RCC against precast concrete panels
(8)	RCC against precast concrete panels with geomembrane
(9)	RCC against precast concrete panels with hot poured membrane
(10)	RCC against precast concrete blocks
(11)	Reinforced conventional concrete cast before RCC placement
(12)	Reinforced conventional concrete cast after RCC placement
(13)	Reinforced concrete cast against precast units or slip-formed facing elements
(14)	Slip-formed/extruded facing elements
(15)	RCC supported by fill shoulders
(16)	Mechanically compacted unformed face of RCC
(17)	Unformed face of RCC
'	GEVR/GE-RCC
*	Stepped face

Pozzolans

(-)	No Pozzolan Used
(C)	High-lime flyash (ASTM Class C)
(F)	Low-lime flyash (ASTM Class F)
(M)	Milled sand
(N)	Natural pozzolan (ASTM Class N)
(R)	ROLAC (mixture of flyash and slag with or without limestone fines)
(S)	Ground-granulated blast-furnace slag
(L)	Mixture of GGBFS and limestone fines