

Dam: Wanjiakouzi

Country: China

River: Gexiang

26°15'59.91"N 104°32'51.89"E

26.266642 104.547745

Owner/Client: China Datang Corporation

Designer/Engineer: Guangxi Provincial Design Institute for Water Conservancy & Hydropower

Contractor: Guangxi Hydropower Construction Bureau

Purpose (code): H

Site start: 01.01.2009

RCC start: 01.01.2012

RCC completion: 31.12.2017

Site completion: 31.12.2018

Height (m): 168

Length (m): 413

Volume of RCC (m³×10³): 760

Total volume (m³×10³): 1020

Reservoir capacity (m³×10⁶): 279

Upstream slope: Unknown

Forming of upstream face (code): Unknown

Downstream slope: Unknown

Forming of downstream face (code): Unknown

Spillway slope: Unknown

Forming of spillway face (code): Unknown

Depth of layers (mm): Unknown

Depth of lifts (mm): Unknown

Cement content (kg/m³): 66

Pozzolan content (kg/m³): 100

Code for pozzolan: (F)

RCCDAM Unique Serial No.: RCCDAM0491

Under Construction



RCCDAM0491UC

Completed Dam



RCCDAM0491CD

Google Earth



RCCDAM0491GE

Guide to Abbreviations

Purpose

- E Environmental
- F Flood control
- G Groundwater recharge
- H Flood control
- I Irrigation
- N Navigation
- P Pollution control
- R Recreation
- W Water supply

Facing method

- (1) Traditional concrete against formwork
- (2) Traditional concrete against formwork with external geomembrane
- (3) RCC against formwork
- (4) RCC against formwork with external geomembrane
- (5) Traditional concrete against precast concrete panels
- (6) Traditional concrete against precast concrete panels with geomembrane
- (7) RCC against precast concrete panels
- (8) RCC against precast concrete panels with geomembrane
- (9) RCC against precast concrete panels with hot poured membrane
- (10) RCC against precast concrete blocks
- (11) Reinforced conventional concrete cast before RCC placement
- (12) Reinforced conventional concrete cast after RCC placement
- (13) Reinforced concrete cast against precast units or slip-formed facing elements
- (14) Slip-formed/extruded facing elements
- (15) RCC supported by fill shoulders
- (16) Mechanically compacted unformed face of RCC
- (17) Unformed face of RCC
 - ' GEVR/GE-RCC
 - * Stepped face

Pozzolans

- (-) No Pozzolan Used
- (C) High-lime flyash (ASTM Class C)
- (F) Low-lime flyash (ASTM Class F)
- (M) Milled sand
- (N) Natural pozzolan (ASTM Class N)
- (R) ROLAC (mixture of flyash and slag with or without limestone fines)
- (S) Ground-granulated blast-furnace slag
- (L) Mixture of GGBFS and limestone fines